

Maxxam™ PP5940 B131 C 600R

Polypropylene

PolyOne Corporation

Message:

Glass fiber and mica reinforced PP compound

General Information			
Filler / Reinforcement	Glass/mica, 40% filler by weight		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ISO 1133
Molding Shrinkage	0.30 - 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	67.0	MPa	ISO 527
Tensile Elongation (Break, 23°C)	2.5	%	ISO 527
Flexural Modulus (23°C)	6700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	5.5	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	155	°C	ISO 75-2/B
1.8 MPa, not annealed	138	°C	ISO 75-2/A
Injection	Nominal Value	Unit	
Drying Temperature	80 - 85	°C	
Drying Time	4.0 - 6.0	hr	
Processing (Melt) Temp	200 - 240	°C	
Mold Temperature	30 - 60	°C	
Injection instructions			

Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

