

# YUPLENE® B380G

Polypropylene Impact Copolymer

SK Global Chemical

Message:

YUPLENE B380G is a propylene impact copolymer designed for injection molding applications. YUPLENE B380G has high stiffness, excellent dimensional stability, good impact strength and has been listed by Underwriters Laboratories (UL). YUPLENE B380G is especially suitable for various electrical appliances such as washing machine parts and refrigerator parts.

General Information			
UL YellowCard	E135809-222660		
Features	Good Dimensional Stability		
	Good Impact Resistance		
	High Flow		
	High Stiffness		
	Impact Copolymer		
Uses	Appliance Components		
	Automotive Applications		
	Containers		
	Electrical/Electronic Applications		
	Industrial Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	28	g/10 min	ASTM D1238
Spiral Flow	> 80.0	cm	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	25.5	MPa	ASTM D638
Tensile Elongation (Break)	< 300	%	ASTM D638
Flexural Modulus	1180	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	44	J/m	
23°C	88	J/m	
Aging	Nominal Value	Unit	Test Method
Accelerated Oven Aging - in Air (150°C)	15.0	day	ASTM D3012
Heat Deflection Temperature	110	°C	ASTM D648
DuPont Impact Strength (-10°C)	> 6.86	J	ASTM D2794

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	150	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

