

LNP™ STAT-KON™ RE0039 compound

Polyamide 66
SABIC Innovative Plastics

Message:

LNP STAT-KON* RE0039 is a compound based on Nylon 66 resin containing 15% Carbon Fiber. Added features of this material include: Electrically Conductive, Flame Retardant.
Also known as: LNP* STAT-KON* Compound RC-1003 FR
Product reorder name: RE0039

General Information			
UL YellowCard	E121562-101282582		
Filler / Reinforcement	Carbon Fiber,15% Filler by Weight		
Features	Electrically Conductive		
	Flame Retardant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm ³	ASTM D792
Molding Shrinkage			
Flow : 24 hr	0.20 to 0.30	%	ASTM D955
Across Flow : 24 hr	0.70 to 0.80	%	ASTM D955
Across Flow : 24 hr	0.68 to 0.78	%	ISO 294-4
Flow : 24 hr	0.17 to 0.26	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.55	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.87	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	17600	MPa	ASTM D638
--	15600	MPa	ISO 527-2/1
Tensile Strength			
Break	206	MPa	ASTM D638
Break	210	MPa	ISO 527-2
Tensile Elongation (Break)	2.2	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	11400	MPa	ASTM D790
--	14200	MPa	ISO 178
Flexural Strength			
--	298	MPa	ASTM D790
--	319	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact			
23°C	75	J/m	ASTM D256
23°C ²	8.7	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	700	J/m	ASTM D4812
23°C ³	46	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	8.10	J	ASTM D3763
--	2.35	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	248	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	228	°C	ISO 75-2/Af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	4.6E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.6E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+6	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
	V-0		

Flame Rating (1.50 mm, Testing by SABIC)	5VA		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	266 to 277	°C	
Middle Temperature	282 to 293	°C	
Front Temperature	293 to 304	°C	
Processing (Melt) Temp	282 to 304	°C	
Mold Temperature	93.3 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT