

# DIC.PPS FZ-6600-A5

Polyphenylene Sulfide

DIC Corporation

## Message:

DIC.PPS FZ-6600-A5 is a polyphenylene sulfide (PPS) product, which contains glass fiber reinforced materials. It can be processed by injection molding and is available in North America or Asia Pacific.

Features include:

flame retardant/rated flame

Good toughness

General Information			
UL YellowCard	E53829-243762		
Filler / Reinforcement	Glass fiber reinforced material		
Features	Good toughness		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.89	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.25	%	ASTM D955
Transverse flow	1.0	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
Class m	100		ASTM D785
Class r	121		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	18000	MPa	ASTM D638
Tensile Strength	150	MPa	ASTM D638
Tensile Elongation (Break)	1.0	%	ASTM D638
Flexural Modulus	17000	MPa	ASTM D790
Flexural Strength	250	MPa	ASTM D790
Compressive Strength	170	MPa	ASTM D695
Coefficient of Friction			ASTM D1894
With Metal-Dynamic	0.35		ASTM D1894
With metal-static	0.35		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	75	J/m	ASTM D256
Unnotched Izod Impact	400	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	265	°C	ASTM D648

CLTE - Flow (-30 to 100°C)	1.8E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (1.60 mm)	16	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	5.00		ASTM D150
Dissipation Factor (1 MHz)	6.0E-3		ASTM D150
Arc Resistance	160	sec	ASTM D495
Comparative Tracking Index (CTI)	190	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94

#### Additional Information

The value shown for Comparative Track Index, UL 746, was tested in accordance with ASTM D3638. Flexural Elongation @ Break, ASTM D790: 1.8%

Injection	Nominal Value	Unit
Rear Temperature	300 - 340	°C
Middle Temperature	300 - 340	°C
Front Temperature	300 - 340	°C
Mold Temperature	120 - 150	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

