

LNP™ STAT-KON™ MD000ISC compound

Polypropylene
SABIC Innovative Plastics

Message:

LNP STAT-KON* MD000ISC is a compound based on Polypropylene resin containing Carbon Powder. Added features of this material include: Electrically Conductive, High Impact.
Also known as: LNP* STAT-KON* Compound M-1 HI
Product reorder name: MD000ISC

General Information			
UL YellowCard	E121562-101282751		
Filler / Reinforcement	Carbon Powder		
Features	Electrically Conductive		
	High Impact Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	0.980	g/cm ³	ASTM D792
--	0.970	g/cm ³	ISO 1183
Molding Shrinkage			ASTM D955, ISO 294-4
Flow : 24 hr	1.6 to 1.8	%	
Across Flow : 24 hr	1.6 to 1.8	%	
Water Absorption (24 hr, 50% RH)	0.030	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	483	MPa	ASTM D638
--	1100	MPa	ISO 527-2/1
Tensile Strength			
Yield	21.8	MPa	ASTM D638
Yield	18.5	MPa	ISO 527-2
Break	17.1	MPa	ASTM D638
Break	17.4	MPa	ISO 527-2
Tensile Elongation			ASTM D638
Yield	9.0	%	
Break	130	%	
Flexural Modulus			
--	1140	MPa	ASTM D790
--	1200	MPa	ISO 178
Flexural Strength			
--	27.5	MPa	ASTM D790

--	27.4	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	830	J/m	ASTM D256
23°C ²	66	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1600	J/m	ASTM D4812
23°C ³	110	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	24.4	J	ASTM D3763
--	31.0	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	81.1	°C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	52.8	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	56.0	°C	ISO 75-2/Af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	1.0E-4	cm/cm/°C	
Transverse : -40 to 40°C	1.2E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	10 to 1.0E+6	ohms	ASTM D257
Static Decay ⁵	10	msec	FTMS 101B
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Rear Temperature	193 to 204	°C	
Middle Temperature	216 to 227	°C	
Front Temperature	238 to 249	°C	
Processing (Melt) Temp	227 to 249	°C	
Mold Temperature	32.2 to 48.9	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	5000V to <50V		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

