

EMERGE™ PC 8230-10

Advanced Resin

Trinseo

Message:

EMERGE™ PC 8230-10 is translucent, ultraviolet light resistance and ignition resistant polycarbonate resin. This resin contains no bromine, chlorine, or phosphate flame retardants and is intended to comply with global environmental standards. It combines mechanical performance and high heat resistance with excellent processing characteristics in injection molded applications.

Applications:

- Information technology equipment
- Electronics and electrical appliances

General Information			
UL YellowCard	E206114-100173343	E213639-100173351	E213639-101021177
	E206114-101021181	E54680-101960393	E54680-101960392
Features	Bromine Free		
	Chlorine Free		
	Flame Retardant		
	Good Processability		
	Good UV Resistance		
Uses	High Heat Resistance		
	Appliances		
Appearance	Electrical/Electronic Applications		
Forms	Translucent		
Processing Method	Pellets		
Physical	Injection Molding		
	Nominal Value	Unit	Test Method
	Density	1.20	g/cm ³ ISO 1183/B
	Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min ISO 1133
Hardness	Molding Shrinkage	0.50 to 0.70	% ISO 294-4
	Nominal Value	Unit	Test Method
	Rockwell Hardness		ISO 2039-2
Mechanical	M-Scale	73	
	R-Scale	118	
Tensile Modulus			
	Nominal Value	Unit	Test Method
	2400	MPa	ISO 527-2/1
Tensile Stress			
Tensile Strain (Break)	Yield	60.0	MPa
	Break	58.0	MPa
	110	%	ISO 527-2/50

Flexural Modulus	2330	MPa	ISO 178
Flexural Stress	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	35	kJ/m ²	ISO 179/1eA
Notched Izod Impact Strength (23°C)	70	kJ/m ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Annealed	140	°C	ISO 75-2/B
1.8 MPa, Unannealed	123	°C	ISO 75-2/A
1.8 MPa, Annealed	137	°C	ISO 75-2/A
Vicat Softening Temperature	143	°C	ISO 306/B50
Ball Indentation Temperature	> 125	°C	IEC 60335-1
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Electric Strength	17	kV/mm	IEC 60243-1
Dielectric Constant			IEC 60250
1 Hz	2.70		
50 Hz	2.70		
Dissipation Factor			IEC 60250
1 Hz	1.0E-3		
50 Hz	1.0E-3		
Comparative Tracking Index (Solution A)	225	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating ¹			UL 94
1.50 mm	V-0		
	V-0		
3.00 mm	5VA		
Glow Wire Flammability Index ²			IEC 60695-2-12
1.00 mm	960	°C	
2.00 mm	960	°C	
3.00 mm	960	°C	
Glow Wire Ignition Temperature ³			IEC 60695-2-13
1.00 mm	800	°C	
2.00 mm	800	°C	
3.00 mm	800	°C	
Oxygen Index ⁴	40	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	

Drying Time	3.0 to 4.0	hr
Processing (Melt) Temp	270 to 310	°C
Mold Temperature	60.0 to 100	°C

NOTE		
1.	This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.	
2.	This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.	
3.	This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.	
4.	This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT