

LNP™ THERMOCOMP™ Noryl_HM3020

compound

Polyphenylene Ether + PS
SABIC Innovative Plastics Europe

Message:

LNP THERMOCOMP NORYL_HM3020 compound is a 30% Glass/Mineral filled, high modulus grade. DTUL 248F (120C). UL94 V-1/5VA rated in black and gray.

General Information			
Filler / Reinforcement	Glass\Mineral,30% Filler by Weight		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
	Grey		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm³	ASTM D792
Molding Shrinkage			Internal Method
Flow : 3.20 mm	0.25	%	
Across Flow : 3.20 mm	0.30	%	
Water Absorption (24 hr)	0.060	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	88		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	108	MPa	ASTM D638
Tensile Elongation ² (Yield)	2.0	%	ASTM D638
Flexural Modulus ³ (100 mm Span)	7580	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 100 mm Span)	145	MPa	ASTM D790
Poisson's Ratio	0.38		ASTM D638
Coefficient of Friction			ASTM D1894
vs. Itself - Static	0.42		
vs. Steel - Static	0.40		
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	35.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	91	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	120	°C	ASTM D648
CLTE			ASTM E831

Flow : -40 to 95°C	2.3E-5	cm/cm/°C	
Transverse : -40 to 95°C	3.4E-5	cm/cm/°C	
RTI Elec	50.0	°C	UL 746
RTI Imp	50.0	°C	UL 746
RTI Str	50.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+17	ohms	ASTM D257
Volume Resistivity	1.0E+17	ohms·cm	ASTM D257
Dielectric Strength (1.60 mm, in Air)	25	kV/mm	ASTM D149
Arc Resistance ⁵	PLC 6		ASTM D495
Comparative Tracking Index (CTI)	PLC 4		UL 746
High Amp Arc Ignition (HAI)	PLC 4		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 3		UL 746
Hot-wire Ignition (HWI)	PLC 0		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.47 mm	V-1		
2.59 mm	5VA		
Injection	Nominal Value	Unit	
Drying Temperature	104 to 110	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	30 to 70	%	
Rear Temperature	260 to 304	°C	
Middle Temperature	271 to 310	°C	
Front Temperature	282 to 316	°C	
Nozzle Temperature	293 to 316	°C	
Processing (Melt) Temp	293 to 316	°C	
Mold Temperature	76.7 to 104	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	20 to 100	rpm	
NOTE			
1.	Type I, 5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	2.6 mm/min		
4.	2.6 mm/min		
5.	Tungsten Electrode		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

