

LNP™ COLORCOMP™ HMG47MDC

compound

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

COLORCOMP* HMG47MDC is a general purpose, injection molding ABS for use in medical applications. Biocompatible (ISO10993). FDA compliant. Gamma & EtO sterilizable.

General Information			
Features	Radiation disinfection		
	Ethylene oxide disinfection		
	Biocompatibility		
	General		
Uses	Medical/nursing supplies		
Agency Ratings	FDA not rated		
	ISO 10993		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
230°C/3.8 kg	5.6	g/10 min	ASTM D1238
220°C/10.0 kg	19	g/10 min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.80	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2280	MPa	ASTM D638
--	2530	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	44.1	MPa	ASTM D638
Yield	50.0	MPa	ISO 527-2/5
Fracture ³	33.8	MPa	ASTM D638
Fracture	35.3	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	2.0	%	ASTM D638
Yield	2.6	%	ISO 527-2/5
Fracture ⁵	24	%	ASTM D638
Fracture	25	%	ISO 527-2/5

Flexural Modulus			
50.0mm span ⁶	2340	MPa	ASTM D790
-- ⁷	2410	MPa	ISO 178
Flexural Stress			
--	76.0	MPa	ISO 178
Yield, 50.0mm span ⁸	72.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
-30°C	130	J/m	ASTM D256
23°C	320	J/m	ASTM D256
-30°C ⁹	8.5	kJ/m ²	ISO 180/1A
23°C ¹⁰	23	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	31.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	94.0	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	80.0	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹¹	80.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	98.0	°C	ASTM D1525 ¹²
--	100	°C	ISO 306/B50
Linear thermal expansion coefficient			
Flow: -40 to 40°C	8.8E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	8.8E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	82 - 93	°C	
Drying Time	2.0 - 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.10	%	
Suggested Shot Size	50 - 70	%	
Rear Temperature	188 - 210	°C	
Middle Temperature	204 - 227	°C	
Front Temperature	216 - 238	°C	
Nozzle Temperature	218 - 260	°C	
Processing (Melt) Temp	218 - 260	°C	
Mold Temperature	49 - 71	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	30 - 60	rpm	
Vent Depth	0.038 - 0.051	mm	
NOTE			
1.	5.0 mm/min		

2.	Type 1, 5.0 mm/min
3.	Type 1, 5.0 mm/min
4.	Type 1, 5.0 mm/min
5.	Type 1, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4
10.	80*10*4
11.	80*10*4 mm
12.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

