

Polypropylene PP 10 CA

Polypropylene

PETKIM Petrokimya Holding A.S.

Message:

Application: General purpose injection moulding applications.

General Information			
Filler / Reinforcement	Calcium Carbonate,10% Filler by Weight		
Uses	General Purpose		
Appearance	White		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Apparent Density	0.45 to 0.53	g/cm ³	ASTM D1895
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0 to 15	g/10 min	ASTM D1238
Additional Information	Nominal Value	Unit	
Filler Content - Calcium Carbonate ¹	9.0 to 11.0	wt%	
NOTE			

1. ASTM C25

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

