

Hypel® PELD20/.920

Low Density Polyethylene

Entec Polymers

Message:

Hypel® PELD20/.920 is a Low Density Polyethylene material. It is available in North America.

Important attributes of Hypel® PELD20/.920 are:

RoHS Compliant

Food Contact Acceptable

Typical application of Hypel® PELD20/.920: Food Contact Applications

General Information			
Features	Food Contact Acceptable		
	Low Density		
Agency Ratings	FDA 21 CFR 177.1520		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.918	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	1.0 to 5.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	11.0	MPa	
Break, 23°C	8.27	MPa	
Tensile Elongation (Break, 23°C)	90	%	ASTM D638
Flexural Modulus - 2% Secant (23°C)	228	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	90.0	°C	ASTM D1525 ¹
NOTE			
1.	Rate A (50°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT