

RTP 2899 X 107551

Polyamide 6
RTP Company

Message:
Nylon 6 Overmolding

General Information			
Uses	overmolding		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.920	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	1.6 - 1.8	%	ASTM D955
Moisture Content		%	
Peel strength-Nylon 6 ¹	4.6	kN/m	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	65		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength ² (Break, 3.20 mm)	2.76	MPa	ASTM D412
Tensile Elongation ³ (Break)	400	%	ASTM D412
Tear Strength ⁴	17.5	kN/m	ASTM D624
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0 - 3.0	hr	
Processing (Melt) Temp	216 - 249	°C	
Mold Temperature	48.9 - 65.6	°C	
Injection Pressure	82.7 - 124	MPa	
Injection instructions			
Desiccant Type Dryer Required.			
NOTE			
1.	90°, 20 in/min, RTP 55, Interface Failure		
2.	C mold, 500 mm/min		
3.	Mouth die C, 500 mm/min		
4.	C mould		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

