

# EL-Lene™ LD1902F

Low Density Polyethylene

SCG Chemicals Co., Ltd.

## Message:

EL-LENE LD1902F is a LDPE resin with Slip and Antiblocking agent.

General Information			
Additive	Antiblock (2400 ppm) Slip (1400 ppm)		
Features	Antiblocking Food Contact Acceptable High Strength Opticals Slip		
Uses	Bags Blending		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.919	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Secant Modulus			ASTM D882
2% Secant, MD : 38 µm	245	MPa	
2% Secant, TD : 38 µm	275	MPa	
Tensile Strength			ASTM D882
TD : Yield, 38 µm	11.8	MPa	
MD : Break, 38 µm	22.6	MPa	
TD : Break, 38 µm	18.6	MPa	
Tensile Elongation			ASTM D882
MD : Break, 38 µm	260	%	
TD : Break, 38 µm	720	%	
Dart Drop Impact (38 µm)	150	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD : 38 µm	370	g	

TD : 38 μm	100	g	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -70.0	°C	ASTM D746
Vicat Softening Temperature	92.0	°C	ASTM D1525
Melting Temperature	110	°C	ASTM D2117
Optical	Nominal Value	Unit	Test Method
Gloss (38.0 μm)	50		ASTM D2457
Haze (38.0 μm)	9.0	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	140 to 170	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

