DISTRUMID 6 GF50

Polyamide 6

Distrupol

Message:

DISTRUMID 6 GF50 is a polyamide 6 (nylon 6) material. This product is available in Europe. The main characteristics of DISTRUMID 6 GF50 are: flame retardant/rated flame.

Forms	Pa	ırticle		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.55		g/cm³	ASTM D792
Molding Shrinkage - Flow	0.20		%	ASTM D955
Water Absorption (24 hr)	0.70		%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	123	115		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength (Ultimate)	190	120	MPa	ASTM D638
Tensile Elongation (Break)	2.0	2.5	%	ASTM D638
Flexural Modulus	13000	7300	MPa	ASTM D790
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, not annealed	220		°C	ASTM D648
1.8 MPa, not annealed	215		°C	ASTM D648
Vicat Softening Temperature	210		°C	ASTM D1525
Melting Temperature	222		°C	
Electrical	Dry	Conditioned	Unit	Test Method
C (D : :::	1.0E+13	1.0E+11	ohms	ASTM D257
Surface Resistivity		1.0E+11	ohms∙cm	ASTM D257
Volume Resistivity	1.0E+15			
<u> </u>	1.0E+15 Dry	Conditioned	Unit	Test Method

干燥

Continuous Service Temperature, S.P., No Stress: 130 °CResistance to Tracking, VDE 0303/1: KC>450 V

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

