

ULTEM™ 2210R resin

Polyether Imide

SABIC Innovative Plastics

Message:

20% Glass fiber filled, enhanced flow Polyetherimide (Tg 217C) with internal mold release. ECO Conforming, UL94 V0 and 5VA listing.

General Information			
UL YellowCard	E121562-502535	E121562-221093	
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Additive	Mold Release		
Features	ECO Compliant		
Agency Ratings	EU Eco		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	9.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	114		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	6890	MPa	ASTM D638
Tensile Strength ² (Break)	140	MPa	ASTM D638
Tensile Elongation ³ (Break)	4.0	%	ASTM D638
Flexural Modulus ⁴ (100 mm Span)	6890	MPa	ASTM D790
Flexural Strength ⁵ (Break, 100 mm Span)	228	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	75	J/m	ASTM D256
Unnotched Izod Impact (23°C)	480	J/m	ASTM D4812
Reverse Notch Izod Impact (3.20 mm)	480	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm	210	°C	
1.8 MPa, Unannealed, 6.40 mm	211	°C	
Vicat Softening Temperature	226	°C	ASTM D1525 ⁶
RTI Elec	170	°C	UL 746
RTI Imp	170	°C	UL 746
RTI Str	170	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Arc Resistance ⁷	PLC 6		ASTM D495
Comparative Tracking Index (CTI)	PLC 4		UL 746
High Amp Arc Ignition (HAI)	PLC 4		UL 746

High Voltage Arc Tracking Rate (HVTR)	PLC 2	UL 746	
Hot-wire Ignition (HWI)	PLC 1	UL 746	
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.406 mm	V-0		
1.91 mm	5VA		
Oxygen Index	50	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	4.0 to 6.0	hr	
Drying Time, Maximum	24	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 60	%	
Rear Temperature	332 to 399	°C	
Middle Temperature	338 to 399	°C	
Front Temperature	343 to 399	°C	
Nozzle Temperature	343 to 399	°C	
Processing (Melt) Temp	349 to 399	°C	
Mold Temperature	135 to 163	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
Vent Depth	0.025 to 0.076	mm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	2.6 mm/min		
5.	2.6 mm/min		
6.	Rate B (120°C/h), Loading 2 (50 N)		
7.	Tungsten Electrode		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT