Mylar® EB-11 (92 guage)

Polyethylene Terephthalate

DuPont Teijin Films U.S.

Message:

Mylar® EB-11 (92 guage) is a Polyethylene Terephthalate (PET) product. It is available in North America. Applications of Mylar® EB-11 (92 guage) include decorative parts, film and labels. Characteristics include: Chemical Resistant Good Toughness Heat Resistant Moisture Resistant

| General Information | | | |
|---------------------------------|--------------------------|-------|-------------|
| UL YellowCard | E93687-252917 | | |
| Features | Good Chemical Resistance | | |
| | Good Thermal Stability | | |
| | Good Toughness | | |
| | Moisture Resistant | | |
| | Platable | | |
| | | | |
| Uses | Decorative Parts | | |
| | Film | | |
| | Labels | | |
| | | | |
| Appearance | Matte Finish | | |
| | Translucent | | |
| | | | |
| Forms | Film | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.39 | g/cm³ | ASTM D1505 |
| Films | Nominal Value | Unit | Test Method |
| Film Thickness - Tested | 23 | μm | |
| Secant Modulus - 1% Secant, MD | 3450 | MPa | ASTM D882 |
| Tensile Strength - MD (Yield) | 124 | MPa | ASTM D882 |
| Tensile Elongation - MD (Break) | 130 | % | ASTM D882 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

