

TECNOBLEND B32

Acrylonitrile Butadiene Styrene + Nylon

Taro Plast S.p.A.

Message:

ABS/PA alloy combining good impact strength, rigidity and chemical resistance with good surface appearance.

General Information			
Features	Rigid, good		
	Impact resistance, good		
	Good chemical resistance		
	Good appearance		
Agency Ratings	EU 2000/53/EC		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (240°C/10.0 kg)	20	g/10 min	ISO 1133
Molding Shrinkage			Internal method
Vertical flow direction: 23°C, 3.20mm	1.1	%	Internal method
Flow direction: 23°C, 3.20mm	1.1	%	Internal method
Water Absorption (Saturation, 23°C)	1.4	%	ISO 62
Granule Humidity ¹		%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	50.0	MPa	ISO 527-2/50
Fracture	45.0	MPa	ISO 527-2/50
Tensile Strain (Break)	40	%	ISO 527-2/50
Flexural Modulus ²	2150	MPa	ISO 178
Flexural Stress ³	72.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	8.5	kJ/m ²	ISO 179/1eA
23°C	14	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C	12	J/m	ASTM D256
-30°C	6.5	kJ/m ²	ISO 180/1A
Notched Izod Impact (23°C)	12.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature ⁴			
0.45 MPa, not annealed	100	°C	ISO 75-2/B
1.8 MPa, not annealed	75.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	150	°C	ISO 306/A50
--	110	°C	ISO 306/B50
CLTE - Flow (-30 to 30°C)	9.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate ⁵ (1.60 mm)	< 100	mm/min	ISO 3795
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	650	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	1.0	hr	
Processing (Melt) Temp	240 - 280	°C	
Mold Temperature	40.0 - 80.0	°C	
Injection Rate	Moderate		
Injection instructions			
Pre-heat Temperature: 80 to 100°CPre-heat Time: 3 hr			
NOTE			
1.	TARO 002		
2.	1.0 mm/min		
3.	1.0 mm/min		
4.	120°C/hr		
5.	US FMVSS302		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT