

SCANAMID 6 B32^E F30

Polyamide 6

Polykemi AB

Message:

Glass fibre-reinforced, Modified

General Information				
UL YellowCard		E122538-101152141	E122538-322179	
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
UL File Number		E122538		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.31	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.90	--	%	
Flow	0.30	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	76	--		ASTM D2240
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress	140	110	MPa	ISO 527-2
Tensile Strain (Break)	4.0	7.0	%	ISO 527-2
Flexural Modulus (23°C)	7500	4800	MPa	ISO 178
Flexural Stress	210	140	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-20°C	13	--	kJ/m ²	
23°C	19	23	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature ¹				
0.45 MPa, Unannealed	210	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	190	--	°C	ISO 75-2/A
Vicat Softening Temperature	> 200	--	°C	ISO 306/B50
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
Glow Wire Ignition Temperature (2.00 mm)	650	--	°C	IEC 60695-2-13
NOTE				

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

