

ELASTOSIL® E 43 N

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, RTV-1

Small Appliances, Household Appliances

Microwave Ovens, Household Appliances

Bonding for HTV, Plastics and Rubber Processing

Coating of Fabrics and Textiles, Technical Textiles

Bonding & Sealing, Adhesives and Sealants

Bonding & Sealing, Mechanical and Plant Engineering

General Information			
Features	General Purpose		
Uses	Adhesives		
	Bonding		
	Sealants		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Translucent		
Density			
--	1.05	g/cm ³	DIN 53217
--	1.10	g/cm ³	ISO 1183
Viscosity	300	Pa · s	DIN EN ISO 3219
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	35		DIN 53505
Tensile Strength	6.00	MPa	DIN 53504
Tensile Elongation at Break	750	%	DIN 53504
Tear Strength	12.0	kN/m	ASTM D624B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 1342475533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT