

Beetle® PET1610F

Polyethylene Terephthalate
Teknor Apex Company (Chem Polymer)

Message:
PET1610F is a reinforced PET containing 50% glass fiber, which has good mechanical properties and excellent mold release at high temperature.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 50% filler by weight		
Features	Good demoulding performance		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.74	g/cm ³	ISO 1183
Molding Shrinkage	0.30 - 0.90	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	19000	MPa	ISO 527-2
Tensile Stress (Yield)	160	MPa	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Modulus	17500	MPa	ISO 178
Flexural Stress	260	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	13	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	40	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	> 220	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Dielectric Strength (3.00 mm)	10	kV/mm	IEC 60243-1
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.57 mm)	HB		UL 94
Oxygen Index	21	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	140	°C	
Drying Time	4.0	hr	
Rear Temperature	275 - 290	°C	
Middle Temperature	275 - 290	°C	

Front Temperature	275 - 290	°C
Processing (Melt) Temp	< 290	°C
Mold Temperature	120 - 140	°C
Injection Rate	Fast	
Screw Speed	50 - 100	rpm

Injection instructions

背压:低注射压力:高

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

