

Kemcor HD 0811

High Density (HMW) Polyethylene
Qenos Pty Ltd

Message:

This resin meets the requirements for unrestricted food contact specified in AS 2070 Part 1 (1992).
Gloss (AS 1326) = 10 GGU

General Information			
Additive	High Antiblock		
	Medium Slip		
Features	Good Impact Resistance		
	Good Tear Strength		
	High Antiblocking		
	High Molecular Weight		
	Medium Slip		
Uses	Bags		
	Film		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.952	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.060	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882
MD : Break	57.0	MPa	
TD : Break	46.0	MPa	
Dart Drop Impact	160	g	ASTM D1709
Optical	Nominal Value	Unit	Test Method
Haze	80	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

