## Karina IVORY PVC COMPOUND TR-700-35/1

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

## Message:

PVC COMPOUND WITH ADDITION OF NITRILE RUBBER RECOMMENDED FOR INJECTION OF SOLES.

General Information			
Uses	Footwear		
Appearance	lvory		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity <sup>1</sup>	1.17 to 1.23	g/cm³	ASTM D792
Color	ОК		ME 12
Color a	-3.59 to 2.41		ME 12
Color b	2.40 to 8.40		ME 12
Color L	79.0 to 85.0		ME 12
Abrasion Resistance	< 130	mm³	DIN 53516
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	68 to 72		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 11.8	МРа	ASTM D638
Tensile Elongation (Yield)	> 300	%	ASTM D638
NOTE			
1.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

