

Polifor® 20 BS/25 NATURALE

Polypropylene Homopolymer

SO.F.TER. SPA

Message:

Polypropylene homopolymer 25% mineral filled

General Information			
Filler / Reinforcement	Mineral,25% Filler by Weight		
Features	Homopolymer		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage	1.3	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	28.0	MPa	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	1800	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	20	J/m	
23°C	40	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	55.0	°C	ASTM D648
Vicat Softening Temperature	92.0	°C	ASTM D1525 ¹
Ball Pressure Test (125°C)	Pass		IEC 335
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Glow Wire Ignition Temperature	650	°C	IEC 60695-2-13
Oxygen Index	21	%	ASTM D2863
Injection	Nominal Value	Unit	
Rear Temperature	180	°C	
Middle Temperature	210	°C	

Front Temperature	220	°C
Mold Temperature	40.0 to 60.0	°C
NOTE		

1. Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

