# T-Blend® 6594B-G82E-1

## Styrene Ethylene Butylene Styrene Block Copolymer

## **TSRC** Corporation

#### Message:

T-Blend® 6594B-G82E-1 is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) product. It is available in Asia Pacific. Applications of T-Blend® 6594B-G82E-1 include wire & cable and engineering/industrial parts.

Characteristics include:

Flame Rated

**RoHS Compliant** 

**WEEE Compliant** 

Eco-Friendly/Green

Flame Retardant

General Information					
Features	Flame Retardant				
	Good Processability				
	Good Surface Finish				
	Halogen Free				
	High Heat Resistance				
	Low Smoke Emission				
	Non-Toxic Recyclable Material				
Uses	Plugs				
	Wire & Cable Applications				
Agency Ratings	EU 2002/96/EC (WEEE)				
	UL Unspecified Rating				
RoHS Compliance	RoHS Compliant				
Appearance	Black				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	0.950 to 0.990	g/cm³	ASTM D792		
Melt Mass-Flow Rate (MFR) (180°C/5.0 kg)	3.3	g/10 min	ASTM D1238		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	80 to 84		ASTM D2240		
Elastomers	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	8.34	МРа	ASTM D412		
Tensile Elongation (Break)	390	%	ASTM D412		
Tear Strength	81.4	kN/m	ASTM D624		
Flammability	Nominal Value		Test Method		

Flame Rating	НВ		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	180 to 220	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

