

Amilan® CM1041LO

Polyamide 6
Toray Resin Company

Message:
Amilan® CM1041LO is a Polyamide 6 (Nylon 6) product. It can be processed by extrusion and is available in Asia Pacific, Europe, or North America.

General Information			
UL YellowCard	E41797-233428		
Processing Method	Extrusion		
Part Marking Code	>PA6<		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.13	g/cm ³	ISO 1183
Water Absorption (23°C, 24 hr)	1.8	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (23°C)	75.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	50	%	ISO 527-2
Flexural Modulus (23°C)	2500	MPa	ISO 178
Flexural Stress (23°C)	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.5	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	225	°C	DSC
Fill Analysis	Nominal Value	Unit	
Melt Viscosity ¹			
250°C	1780	Pa·s	
270°C	1110	Pa·s	
290°C	770	Pa·s	
NOTE			

1. Koka Type Flow Tester

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT