# Lucky Enpla LPB1000

### Polybutylene Terephthalate

#### Lucky Enpla Co LTD

#### Message:

Lucky Enpla LPB1000 is a polybutene terephthalate (PBT) product. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. Lucky Enpla LPB1000 applications include electrical/electronic applications and the automotive industry.

General Information			
Features	General		
Uses	Electrical/Electronic Applications		
	Connector		
	Application in Automobile Field		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm³	ASTM D792
Molding Shrinkage - Flow	1.2 - 2.1	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup>	53.9	MPa	ASTM D638
Flexural Modulus <sup>2</sup>	2260	MPa	ASTM D790
Flexural Strength <sup>3</sup>	83.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (3.18 mm)	29	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	154	°C	ASTM D648
1.8 MPa, not annealed	57.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Rear Temperature	230 - 250	°C	
Middle Temperature	240 - 260	°C	
Front Temperature	240 - 260	°C	
Nozzle Temperature	240 - 260	°C	
Mold Temperature	50.0 - 70.0	°C	
Back Pressure	0.490 - 2.94	MPa	
Screw Speed	30 - 60	rpm	
Injection instructions			
Resin Temperature: 250-270°CInjection	Pressure (1st Pressure): 600-1100	kg/cm <sup>2</sup> Injection Pressure (2nd Pres	ssure): 400-800 kg/cm²

1.	50 mm/min
2.	10 mm/min
3.	10 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

