

Crastin® SK692FR NC010

THERMOPLASTIC POLYESTER RESIN

DuPont Performance Polymers

Message:

15% Glass Reinforced, Flame Retardant, Polybutylene Terephthalate

General Information			
UL YellowCard	E41938-100191678		
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Agency Ratings	UL Unspecified Rating		
Forms	Pellets		
Processing Method	Injection Molding		
Multi-Point Data	Shear Stress vs. Shear Rate (ISO 11403-1)		
	Specific Volume vs Temperature (ISO 11403-2)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Part Marking Code (ISO 11469)	>PBT-GF15FR(17)<		
Physical	Nominal Value	Unit	Test Method
Density	1.55	g/cm³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	1.0	%	
Flow	0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7000	MPa	ISO 527-2
Tensile Stress (Break)	115	MPa	ISO 527-2
Tensile Strain (Break)	2.7	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.8	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	38	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	199	°C	ISO 75-2/A
Melting Temperature ¹	223	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Comparative Tracking Index (CTI) (0.750 mm)	PLC 3		UL 746
Comparative Tracking Index	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20

0.800 mm	V-0	
1.50 mm	V-0	
Fill Analysis	Nominal Value	Unit
Melt Density	1.31	g/cm ³
NOTE		
1.	10°C/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

