

ULTEM™ HU1110 resin

Polyether Imide

SABIC Innovative Plastics

Message:

Enhanced flow Polyetherimide (Tg 217°C). ECO Conforming. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO 10993 or USP Class VI), food contact compliant. EtO and steam sterilizable. NSF 51 listing, compliant in recognized colors.

General Information			
UL YellowCard	E121562-100044748		
Features	Biocompatible		
	ECO Compliant		
	Ethylene Oxide Sterilizable		
	Food Contact Acceptable		
	High Flow		
	Steam Sterilizable		
Uses	Medical/Healthcare Applications		
	Pharmaceuticals		
Agency Ratings	EU Eco		
	ISO 10993		
	NSF 51		
	USP Class VI		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.36	g/cm ³	ASTM D792
--	1.27	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	16	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (360°C/5.0 kg)	21.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	1.2	%	
Equilibrium, 23°C, 50% RH	0.65	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	3720	MPa	ASTM D638
--	3500	MPa	ISO 527-2/1
Tensile Strength			

Yield ²	110	MPa	ASTM D638
Yield	110	MPa	ISO 527-2/5
Break ³	85.0	MPa	ASTM D638
Tensile Elongation			
Yield ⁴	7.0	%	ASTM D638
Yield	6.0	%	ISO 527-2/5
Break ⁵	70	%	ASTM D638
Break	60	%	ISO 527-2/5
Flexural Modulus			
100 mm Span ⁶	3720	MPa	ASTM D790
50.0 mm Span ⁷	3420	MPa	ASTM D790
-- ⁸	3300	MPa	ISO 178
Flexural Stress			
--	140	MPa	ISO 178
Yield, 50.0 mm Span ⁹	174	MPa	ASTM D790
Yield, 100 mm Span ¹⁰	165	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹¹ (23°C)	5.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C	56	J/m	ASTM D256
-30°C ¹²	4.0	kJ/m ²	ISO 180/1A
23°C ¹³	4.0	kJ/m ²	ISO 180/1A
Reverse Notch Izod Impact (3.20 mm)	1900	J/m	ASTM D256
Instrumented Dart Impact (23°C, Total Energy)	28.0	J	ASTM D3763
Gardner Impact (23°C)	23.0	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 6.40 mm	199	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹⁴	210	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	219	°C	ASTM D1525 ¹⁵
--	200	°C	ISO 306/B50
--	205	°C	ISO 306/B120
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	5.5E-5	cm/cm/°C	
Transverse : -40 to 40°C	5.5E-5	cm/cm/°C	
RTI Elec	170	°C	UL 746
RTI Imp	170	°C	UL 746
RTI Str	170	°C	UL 746
Electrical	Nominal Value		Test Method
Arc Resistance ¹⁶	PLC 5		ASTM D495

Comparative Tracking Index (CTI)	PLC 4	UL 746
High Amp Arc Ignition (HAI)	PLC 3	UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 2	UL 746
Hot-wire Ignition (HWI)	PLC 1	UL 746
Flammability	Nominal Value	Test Method
Flame Rating		UL 94
0.710 mm	V-2	
0.750 mm	V-0	
3.00 mm	5VA	
Injection	Nominal Value	Unit
Drying Temperature	149	°C
Drying Time	4.0 to 6.0	hr
Drying Time, Maximum	24	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 to 60	%
Rear Temperature	332 to 399	°C
Middle Temperature	338 to 399	°C
Front Temperature	343 to 399	°C
Nozzle Temperature	343 to 399	°C
Processing (Melt) Temp	349 to 399	°C
Mold Temperature	135 to 163	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm
Vent Depth	0.025 to 0.076	mm
NOTE		
1.	5.0 mm/min	
2.	Type I, 5.0 mm/min	
3.	Type I, 5.0 mm/min	
4.	Type I, 5.0 mm/min	
5.	Type I, 5.0 mm/min	
6.	2.6 mm/min	
7.	1.3 mm/min	
8.	2.0 mm/min	
9.	1.3 mm/min	
10.	2.6 mm/min	
11.	80*10*4 sp=62mm	
12.	80*10*4	
13.	80*10*4	
14.	80*10*4 mm	
15.	Rate B (120°C/h), Loading 2 (50 N)	
16.	Tungsten Electrode	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

