Greenflex® ML 60 F

Ethylene Vinyl Acetate Copolymer

Versalis S.p.A.

Message:

Greenflex ML 60 F is an ethylene vinyl acetate copolymer (EVA) for injection moulding, compounding and extrusion. Main Application

Greenflex ML 60 F is recommended for the production of foamed and crosslinked sheets for shoes and gasket.

General Information				
Features	Copolymer			
	Foamable			
	Food Contact Acceptable			
Uses	Foam			
	Footwear			
	Gaskets			
	Sheet			
Agency Ratings	EU Food Contact, Unspecified Rating			
Forms	Pellets			
Processing Method	Compounding			
	Extrusion			
	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	0.952	g/cm³	ISO 1183	
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.5	g/10 min	ISO 1133	
Vinyl Acetate Content	28.0	wt%	Internal Method	
Hardness	Nominal Value	Unit	Test Method	
Shore Hardness			ISO 868	
Shore A, Injection Molded	75			
Shore D, Injection Molded	32			
Mechanical	Nominal Value	Unit	Test Method	
	Nominal Value 3.00	Unit MPa	Test Method ISO 527-2	
Tensile Stress (Yield, Injection Molded)				
Mechanical Tensile Stress (Yield, Injection Molded) Flexural Modulus (Injection Molded) Thermal	3.00	MPa	ISO 527-2	
Tensile Stress (Yield, Injection Molded) Flexural Modulus (Injection Molded)	3.00	MPa MPa	ISO 527-2 ISO 178	
Tensile Stress (Yield, Injection Molded) Flexural Modulus (Injection Molded) Thermal	3.00 10.0 Nominal Value	MPa MPa Unit	ISO 527-2 ISO 178 Test Method	
Tensile Stress (Yield, Injection Molded) Flexural Modulus (Injection Molded) Thermal Brittleness Temperature	3.00 10.0 Nominal Value < -80.0	MPa MPa Unit	ISO 527-2 ISO 178 Test Method ASTM D746	

Processing (Melt) Temp	140 to 190	°C	
Mold Temperature	10.0 to 30.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2