

Lupoy® 3030-10

Polycarbonate

LG Chem Ltd.

Message:

LUPOY PC 3030-10 resin is designed for injection molding products. It exhibits an excellent physical property balance of heat resistance, transparency and impact strength.

General Information			
UL YellowCard	E67171-100907372		
Additive	UV Stabilizer		
Features	Good Chemical Resistance		
	Good Flow		
	Good Impact Resistance		
	High Clarity		
	High Heat Resistance		
	Ultra High Toughness		
Uses	Appliances		
	Electrical/Electronic Applications		
	Thin-walled Parts		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Spiral Flow	2.20	cm	
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption			ASTM D570
23°C, 24 hr	0.15	%	
Equilibrium, 23°C, 50% RH	0.32	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	73		
R-Scale	118		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2400	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield, 23°C ¹	62.0	MPa	
Break	60.0	MPa	

Tensile Elongation			ASTM D638
Yield	6.0	%	
Break	100	%	
Flexural Modulus	2400	MPa	ASTM D790
Flexural Strength	96.0	MPa	ASTM D790
Taber Abrasion Resistance - Change in Haze ²	45	%	ASTM D1004
Average Extent of Burning	3	cm	ASTM D635
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ³ (23°C, 3.20 mm)	930	J/m	ASTM D256
Unnotched Izod Impact (23°C)	No Break		ASTM D256
Instrumented Dart Impact ⁴ (23°C, 3.20 mm, Total Energy)	87.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Annealed, 4.00 mm	144	°C	
1.8 MPa, Unannealed, 4.00 mm	128	°C	
1.8 MPa, Annealed, 4.00 mm	141	°C	
Vicat Softening Temperature	149	°C	ASTM D1525 ⁵
Ball Indentation Temperature	> 125	°C	IEC 60598-1
CLTE - Flow (-40 to 82°C)	6.8E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	2.0E+17	ohms·cm	ASTM D257
Dielectric Strength	17	kV/mm	ASTM D149
Dielectric Constant (60 Hz)	3.00		ASTM D150
Dissipation Factor (60 Hz)	1.0E-3		ASTM D150
Comparative Tracking Index (2.00 mm)	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm	HB		
0.500 mm	V-2		
2.50 mm	V-2		
Glow Wire Ignition Temperature ⁶ (2.00 mm)	850	°C	IEC 60695-2-13
Oxygen Index	26	%	ASTM D2863
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance	89.0	%	ASTM D1003
Haze	0.70 to 1.5	%	ASTM D1003
NOTE			
1.	50 mm/min		
2.	1000g, 500 cycles, CS-10F Wheel		
3.	0.25 mm Notch Depth		

4.	3.38 m/sec
5.	Rate A (50°C/h), Loading 2 (50 N)
6.	5 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

