

ALCOM® PP 620/40 IM UV WT1026-13MCX

Polypropylene
ALBIS PLASTIC GmbH

Message:

ALCOM®PP 620/40 IM UV WT1026-13MCX is a polypropylene product. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. ALCOM®The application fields of PP 620/40 IM UV WT1026-13MCX include building applications, electrical/electronic applications, housing and sporting goods.

Features include:

- Comply with REACH standard
- ROHS certification
- Impact modification
- UV stability

General Information			
Additive	Impact modifier		
	UV stabilizer		
Features	Impact modification		
Uses	Electrical/Electronic Applications		
	Building materials		
	Architectural application field		
	Sporting goods		
	Shell		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	20.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	850	MPa	ISO 527-2
Flexural Modulus	750	MPa	ISO 178
Flexural Stress	21.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
--	48	kJ/m ²	ISO 179/1eA
-40°C	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
--	No Break		ISO 179/1eU
-40°C	100	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	48.0	°C	ISO 75-2/A
Vicat Softening Temperature	45.0	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature			
Dehumidification desiccant	80 - 100	°C	
Hot air dryer	80 - 100	°C	
Drying Time			
Dehumidification desiccant	2.0 - 4.0	hr	
Hot air dryer	2.0 - 3.0	hr	
Processing (Melt) Temp	200 - 270	°C	
Mold Temperature	20 - 70	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

