

ASTAPET™ PC/PET MDA267-A

Polyethylene Terephthalate
Marplex Australia Pty. Ltd.

Message:

ASTAPET™ MDA267 is an alloy of Polycarbonate and 100% recycled polyethylene terephthalate (PET). It is suitable for injection moulding or extrusion.
Note: The letters "U" or "W" indicate UV stabilisation has been added [ie: Astapet™ MDA267-U]. ASTAPET™ MDA267 is a development grade, the typical values detailed on this data sheet are based on limited data and are subject to frequent review

General Information			
Recycled Content	Yes, 100%		
Appearance	Natural color		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
250°C/2.16 kg	2.0	g/10 min	ASTM D1238
285°C/2.16 kg	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow ¹ (3.00 mm)	0.40 - 0.80	%	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	112		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (3.20 mm)	50.0	MPa	ASTM D638
Tensile Elongation ³ (Break, 3.20 mm)	200	%	ASTM D638
Flexural Modulus ⁴ (3.20 mm)	2200	MPa	ASTM D790
Flexural Strength ⁵ (3.20 mm)	76.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	900	J/m	ASTM D256
Dart Drop Impact (3.20 mm)	70.0	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, unannealed, 3.20mm	86.0	°C	ASTM D648
1.8 MPa, unannealed, 12.7mm	105	°C	ASTM D648
Vicat Softening Temperature	155	°C	ASTM D1525 ⁶
CLTE - Flow	6.5E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Additional Information			

CLTE, ASTM D696: 6e-5 to 7e-5 cm/cm/°C Elongation at Break, ASTM D638, 3.2 mm, 5.0 mm/min: >200% Glow Wire Temperature, AS 2420, 1.6 mm: 550°C

Extrusion	Nominal Value	Unit
Drying Temperature	120 - 130	°C
Drying Time	4.0 - 6.0	hr
Cylinder Zone 1 Temp.	200 - 220	°C
Cylinder Zone 2 Temp.	230 - 240	°C
Cylinder Zone 3 Temp.	240 - 250	°C
Cylinder Zone 4 Temp.	245 - 255	°C
Cylinder Zone 5 Temp.	250 - 260	°C
Melt Temperature	240 - 260	°C
Die Temperature	250 - 260	°C
Take-Off Roll	75.0 - 100	°C
Back Pressure	10.0 - 25.0	MPa

NOTE

- | | |
|----|------------|
| 1. | D2 type |
| 2. | 5.0 mm/min |
| 3. | 5.0 mm/min |
| 4. | 1.3 mm/min |
| 5. | 1.3 mm/min |
| 6. | 压力1 (10N) |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT