

Exceed™ 1012 HA mVLDPE

Metallocene Polyethylene Resin
ExxonMobil Chemical

Message:

EXCEED 1012 HA resin is a metallocene ethylene-hexene copolymer. Films made from this resins have outstanding cold temperature toughness, impact strength and puncture. These superior strength properties, along with excellent heat sealing and hot tack performance, make this a very versatile packaging film resin.

General Information			
Additive		Processing aid heat stabilizer	
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD	118	MPa	ASTM D882
1% secant, TD	125	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield	6.97	MPa	ASTM D882
TD: Yield	6.77	MPa	ASTM D882
MD: Fracture	57.2	MPa	ASTM D882
TD: Fracture	55.2	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	450	%	ASTM D882
TD: Fracture	600	%	ASTM D882
Dart Drop Impact	> 1400	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	200	g	ASTM D1922
TD	310	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	30		ASTM D2457
Haze	24	%	ASTM D1003
Additional Information			
Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.			
Legal statement			

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT