

LNP™ LUBRILOY™ D20001 compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP LUBRILOY* D20001 is a compound based on Polycarbonate resin containing Proprietary Lubricant. Added features of this material include: Flame Retardant. Wear Resistant.

Also known as: LNP* LUBRILOY* Compound D-FR ECO

Product reorder name: D20001

General Information			
UL YellowCard	E121562-101283819		
Additive	Lubricant		
Features	Flame Retardant		
	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183, ASTM D792
Molding Shrinkage			
Flow : 24 hr	0.50	%	ASTM D955
Across Flow : 24 hr	0.60	%	ASTM D955
Across Flow : 24 hr	0.57	%	ISO 294-4
Flow : 24 hr	0.53	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.12	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2550	MPa	ASTM D638
--	2600	MPa	ISO 527-2/1
Tensile Strength			
Yield	67.3	MPa	ASTM D638
Yield	62.3	MPa	ISO 527-2
Break	60.2	MPa	ASTM D638
Break	54.5	MPa	ISO 527-2
Tensile Elongation			
Yield	4.5	%	ASTM D638
Yield	4.3	%	ISO 527-2
Break	6.5	%	ASTM D638
Break	6.7	%	ISO 527-2
Flexural Modulus			

--	2830	MPa	ASTM D790
--	2800	MPa	ISO 178
Flexural Strength			
--	103	MPa	ASTM D790
--	102	MPa	ISO 178
Coefficient of Friction			
vs. Itself - Dynamic	0.29		
vs. Itself - Static	0.16		
Wear Factor - Washer	10.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	64	J/m	ASTM D256
23°C ²	6.9	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1600	J/m	ASTM D4812
23°C ³	100	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Energy at Peak Load)	51.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	97.2	°C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	89.4	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	94.0	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	6.6E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.7E-5	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	249 to 260	°C	
Middle Temperature	254 to 266	°C	
Front Temperature	260 to 271	°C	
Processing (Melt) Temp	254 to 288	°C	
Mold Temperature	37.8 to 65.6	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		

3.	80*10*4
4.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

