

STAR-THERM® W A-2X1 HT

Polyamide 66

EPIC Polymers

Message:

STAR-THERM® W A-2X1 HT is a Polyamide 66 (Nylon 66) product. It is available in Europe.

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.75	g/cm³	ISO 1183
Molding Shrinkage - Flow	0.25	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.80	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	13000	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	150	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.0	%	ISO 527-2
Flexural Modulus (23°C)	12500	MPa	ISO 178
Flexural Stress (23°C)	180	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12	kJ/m²	ISO 179
Charpy Unnotched Impact Strength (23°C)	50	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	255	°C	ISO 75-2/B
1.8 MPa, Unannealed	253	°C	ISO 75-2/A
Thermal Conductivity	3.5	W/m/K	ISO 22007
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	270 to 300	°C	
Cylinder Zone 2 Temp.	270 to 300	°C	
Cylinder Zone 3 Temp.	285 to 310	°C	
Cylinder Zone 4 Temp.	285 to 320	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

