

# Tenite™ Propionate 360E0096916 Natural, Trsp

Cellulose Acetate Propionate

Eastman Chemical Company

Message:

Tenite™ cellulosic plastics are noted for their excellent balance of properties - toughness, hardness, strength, surface gloss, clarity, and a warm feel. The mechanical properties of Tenite™ cellulosic plastics differ with plasticizer levels. Lower plasticizer content yields a harder surface, higher heat resistance, greater rigidity, higher tensile strength, and better dimensional stability. Higher plasticizer content increases impact strength. Tenite™ cellulosic plastics are available in natural, clear, selected ambers or smoke transparents and black translucent. Color concentrates are available in let-down ratios from 10:1 to 40:1. Tenite™ Cellulose Acetate Propionate 360-16 has a plasticizer level of 16%. It meets FDA requirements for certain food-contact applications when supplied in specific FDA color numbers.

| General Information |                                      |
|---------------------|--------------------------------------|
| Additive            | Plasticizer (16%)                    |
| Features            | Food Contact Acceptable              |
|                     | Good Strength                        |
|                     | Good Toughness                       |
|                     | High Clarity                         |
|                     | High Gloss                           |
|                     | High Hardness                        |
|                     | Plasticized                          |
|                     | Renewable Resource Content           |
|                     | Soft                                 |
| Uses                | Cosmetic Packaging                   |
|                     | Decorative Displays                  |
|                     | Eyeglass Frames                      |
|                     | Eyeglasses                           |
|                     | Furniture                            |
|                     | Household Goods                      |
|                     | Personal Care                        |
|                     | Plumbing Parts                       |
|                     | Safety Guards                        |
|                     | Sporting Goods                       |
|                     | Toothbrush Handles                   |
|                     | Toys                                 |
|                     | Tubing                               |
|                     | Writing Instruments                  |
| Agency Ratings      | FDA Food Contact, Unspecified Rating |
| Appearance          | Amber                                |
|                     | Black                                |
|                     | Clear/Transparent                    |

Natural Color

| Forms  | Pellets                             |                   |             |
|--|-------------------------------------|-------------------|-------------|
| Physical                                       | Nominal Value                       | Unit              | Test Method |
| Specific Gravity                               | 1.19                                | g/cm <sup>3</sup> | ASTM D792   |
| Molding Shrinkage - Flow                       | 0.20 to 0.60                        | %                 | ASTM D955   |
| Water Absorption (23°C, 24 hr)                 | 1.4                                 | %                 | ASTM D570   |
| Hardness                                       | Nominal Value                       | Unit              | Test Method |
| Rockwell Hardness (R-Scale, 23°C)              | 68                                  |                   | ASTM D785   |
| Mechanical                                     | Nominal Value                       | Unit              | Test Method |
| Tensile Strength                               |                                     |                   | ASTM D638   |
| Yield, 23°C                                    | 26.9                                | MPa               |             |
| Break, 23°C                                    | 30.3                                | MPa               |             |
| Tensile Elongation (Break, 23°C)               | 45                                  | %                 | ASTM D638   |
| Flexural Modulus (23°C)                        | 1240                                | MPa               | ASTM D790   |
| Flexural Strength (Yield, 23°C)                | 35.2                                | MPa               | ASTM D790   |
| Impact   | Nominal Value                       | Unit              | Test Method |
| Notched Izod Impact                            |                                     |                   | ASTM D256   |
| -40°C  | 120                                 | J/m               |             |
| 23°C   | > 530                               | J/m               |             |
| Thermal  | Nominal Value                       | Unit              | Test Method |
| Deflection Temperature Under Load <sup>1</sup> |                                     |                   | ASTM D648   |
| 0.45 MPa, Annealed                             | 80.0                                | °C                |             |
| 1.8 MPa, Annealed                              | 72.0                                | °C                |             |
| Vicat Softening Temperature <sup>2</sup>       | 92.0                                | °C                | ASTM D1525  |
| CLTE - Flow (23°C)                             | 2.0E-5                              | cm/cm/°C          | ASTM D696   |
| Specific Heat (23°C)                           | 1260 to 1670                        | J/kg/°C           | DSC         |
| Thermal Conductivity <sup>3</sup> (23°C)       | 0.25                                | W/m/K             | ASTM C177   |
| Electrical                                     | Nominal Value                       | Unit              | Test Method |
| Dielectric Strength (23°C)                     | 12 to 19                            | kV/mm             | ASTM D149   |
| Dielectric Constant (23°C, 1 MHz)              | 3.30 to 3.80                        |                   | ASTM D150   |
| Dissipation Factor (23°C, 1 MHz)               | 0.010 to 0.15                       |                   | ASTM D150   |
| Optical  | Nominal Value                       | Unit              | Test Method |
| Refractive Index                               | 1.460 to 1.490                      |                   | ASTM D542   |
| Transmittance (1520 µm)                        | > 90.0                              | %                 | ASTM D1003  |
| Haze (1520 µm)                                 | < 8.5                               | %                 | ASTM D1003  |
| Additional Information                         | Nominal Value                       | Unit              | Test Method |
| Soluble Matter Loss (23°C)                     | 0.10                                | %                 | ASTM D570   |
| Weight Loss on Heating - 72 hrs (80°C)         | 1.3                                 | %                 | ASTM D1562  |
| NOTE   |                                     |                   |             |
| 1.   | Conditioned 4 hours at 70°C (158°F) |                   |             |

|    |  |
|----|--|
| 2. | Conditioned 4 hours at 70°C<br>(158°F) |
| 3. | Range: 0.17 to 0.33                    |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

