

Sarlink® TPE ME-2385N

Thermoplastic Elastomer

Teknor Apex Company

Message:

Sarlink®TPE ME-2385N is a thermoplastic elastomer (TPE) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.

Sarlink®The main features of TPE ME-2385N are:

high gloss

daylight resistance

Sarlink®The typical application field of TPE ME-2385N is: automobile industry

General Information			
Features	Low Specific Gravity		
	Sunlight Resistant		
	Low density		
	Highlight		
	smoothness		
	Light stabilization		
	Medium liquidity		
	Lubrication		
	Fill		
	UV absorption		
Uses	Application in Automobile Field		
	Automotive exterior parts		
	Car exterior decoration		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ISO 868
Shore A, 1 second, injection molding	86		ISO 868
Shore A, 5 seconds, injection molding	84		ISO 868
Shore A, 15 seconds, injection molding	81		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹			ISO 37
Transverse flow: 100% strain	3.62	MPa	ISO 37

Flow: 100% strain	4.39	MPa	ISO 37
Tensile Stress ²			ISO 37
Transverse flow: Fracture	13.8	MPa	ISO 37
Flow: Fracture	9.10	MPa	ISO 37
Tensile Elongation ³			ISO 37
Transverse flow: Fracture	830	%	ISO 37
Flow: Fracture	620	%	ISO 37
Tear Strength ⁴			ISO 34-1
Transverse flow	43	kN/m	ISO 34-1
Flow	46	kN/m	ISO 34-1
Compression Set ⁵			ISO 815
23°C, 22 hr	20	%	ISO 815
70°C, 22 hr	32	%	ISO 815
90°C, 70 hr	37	%	ISO 815
125°C, 70 hr	49	%	ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ⁶			ISO 188
Transverse flow: 110°C, 1008 hr	-4.5	%	ISO 188
Flow: 110°C, 1008 hr	-14	%	ISO 188
Transverse flow: 100% strain 110°C, 1008 hr	7.9	%	ISO 188
Flow: 100% strain 110°C, 1008 hr	12	%	ISO 188
Transverse flow: 125°C, 168 hr	-2.9	%	ISO 188
Flow: 125°C, 168 hr	-18	%	ISO 188
Transverse flow: 100% strain 125°C, 168 hr	6.9	%	ISO 188
Flow: 100% strain 125°C, 168 hr	13	%	ISO 188
Change in Tensile Strain at Break in Air ⁷			ISO 188
Transverse flow: 110°C, 1008 hr	-3.6	%	ISO 188
Flow: 110°C, 1008 hr	-16	%	ISO 188
Transverse flow: 125°C, 168 hr	-4.7	%	ISO 188
Flow: 125°C, 168 hr	-20	%	ISO 188
Change in Shore Hardness in Air			ISO 188
Support a, 110°C, 1008 hr ⁸	3.6		ISO 188
Support a, 110°C, 1008 hr	3.8		ISO 188
Support a, 110°C, 1008 hr ⁹	2.7		ISO 188
Support a, 125°C, 168 hr ¹⁰	3.4		ISO 188
Support a, 125°C, 168 hr ¹¹	3.1		ISO 188
Support a, 125°C, 168 hr ¹²	2.5		ISO 188
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 206 sec ⁻¹)	192	Pa · s	ASTM D3835
Additional Information			
雾化,3小时,100C,21C板 = 98%			

Injection	Nominal Value	Unit
Rear Temperature	199 - 210	°C
Middle Temperature	204 - 216	°C
Front Temperature	210 - 221	°C
Nozzle Temperature	216 - 227	°C
Processing (Melt) Temp	216 - 227	°C
Mold Temperature	35.0 - 65.6	°C
Injection Pressure	1.38 - 6.89	MPa
Injection Rate	Fast	
Back Pressure	0.172 - 0.862	MPa
Screw Speed	50 - 120	rpm
Cushion	3.81 - 25.4	mm

Injection instructions

无需干燥.但如果湿度过大,则将粒料在150°F (65°C)的温度下干燥2-4小时.

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	193 - 204	°C
Cylinder Zone 2 Temp.	199 - 210	°C
Cylinder Zone 3 Temp.	204 - 216	°C
Cylinder Zone 5 Temp.	210 - 221	°C
Die Temperature	216 - 227	°C

Extrusion instructions

螺杆转速30 - 100 rpm

NOTE	
1.	Type 1, 510mm/min
2.	Type 1, 510mm/min
3.	Type 1, 510mm/min
4.	B method, right angle specimen (without cut), 510mm/min
5.	Type a
6.	Type 1
7.	Type 1
8.	5 sec
9.	1 sec
10.	15 sec
11.	5 sec
12.	1 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

