

Sasol Polymers PP CRV648

Polypropylene Impact Copolymer

Sasol Polymers

Message:

- Features
- High flow
- Narrow molecular weight distribution
- Particularly suitable for injection moulding of thin walled articles, requiring very good low temperature impact resistance and good stiffness
- Applications
- Injection moulding
- Ice cream tubs
- Paint containers
- Shopping baskets
- Buckets / pails
- Storage boxes
- Luggage

General Information			
Additive	Nucleating agent		
	Antistatic property		
	Unspecified additive		
Features	Nucleated		
	Rigid, good		
	Impact copolymer		
	Antistatic property		
	High liquidity		
	Low temperature impact resistance		
	Compliance of Food Exposure		
Uses	Thin wall parts		
	Leather case		
	Container		
	Food container		
	Barrel		
Agency Ratings	EC 1935/2004		
	FDA 21 CFR 177.1520(a)(3)(i)(c)(1)		
	FDA 21 CFR 177.1520(c) 3.1a		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method

Density	0.904	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	24	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction	1.3	%	ISO 294-4
Flow direction	1.3	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	42.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1000	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	20.0	MPa	ISO 527-2/1A/50
Tensile Strain			ISO 527-2/1A/50
Yield	6.5	%	ISO 527-2/1A/50
Fracture	> 50	%	ISO 527-2/1A/50
Flexural Modulus	950	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	6.0	kJ/m ²	ISO 179/1eA
0°C	8.0	kJ/m ²	ISO 179/1eA
23°C	12	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	76.0	°C	ISO 75-2/B
1.8 MPa, not annealed	46.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	142	°C	ISO 306/A120
--	54.0	°C	ISO 306/B120
Melting Temperature	163	°C	ISO 11357-3
Injection	Nominal Value	Unit	
Hopper Temperature	40.0 - 60.0	°C	
Rear Temperature	180 - 260	°C	
Middle Temperature	220 - 280	°C	
Front Temperature	240 - 280	°C	
Nozzle Temperature	220 - 280	°C	
Processing (Melt) Temp	220 - 280	°C	
Mold Temperature	20.0 - 60.0	°C	
Injection instructions			

Zone 4: 240 to 280°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

