# **AMTOPP BA30**

## Polypropylene Inteplast Group

### Message:

General Purpose CoEx Heat Sealable
BIAXIALLY ORIENTED POLYPROPYLENE FILM TWO SIDE SEALABLE FOR FOOD PACKAGING

| General Information                      |                 |            |             |
|--|-----------------|------------|-------------|
| Uses                                     | Film            |            |             |
|  | Food Packaging  |            |             |
| Dhyrical                                 | Naminal Value   | Unit       |             |
| Physical                                 | Nominal Value   | Unit       |             |
| Dimensional Stability                    |                 |            |             |
| Across Flow, 130°C <sup>1</sup>          | < 3.0           | %          |             |
| Flow, 130°C <sup>2</sup>                 | < 5.0           | %          |             |
| Mechanical                               | Nominal Value   | Unit       | Test Method |
| Coefficient of Friction (Dynamic)        | 0.20            |            | ASTM D1894  |
| Films                                    | Nominal Value   | Unit       | Test Method |
| Film Thickness - Tested                  | 30              | μm         |             |
| Tensile Strength                         |                 |            | ASTM D882   |
| MD : Yield                               | 117             | MPa        |             |
| TD : Yield                               | 207             | MPa        |             |
| Tensile Elongation                       |                 |            | ASTM D882   |
| MD : Break                               | 190             | %          |             |
| TD : Break                               | 70              | %          |             |
| Water Vapor Transmission Rate (38°C, 909 |                 |            |             |
| RH)                                      | 4.7             | g/m²/24 hr | ASTM F1249  |
| Yield <sup>3</sup>                       | 36.6            | m²/kg      |             |
| Heat Seal Temperature <sup>4</sup>       |                 |            |             |
| Treated Side                             | 121             | °C         |             |
| Untreated side                           | 104             | °C         |             |
| Surface Energy                           | 38              | dyne/cm    | ASTM D2578  |
| Optical                                  | Nominal Value   | Unit       | Test Method |
| Gloss (45°)                              | 85              |            | ASTM D2457  |
| Haze                                     | 2.0             | %          | ASTM D1003  |
| NOTE                                     |                 |            |             |
| 1.                                       | 5 minuites      |            |             |
| 2.                                       | 5 minutes       |            |             |
| 3.                                       | Internal Method |            |             |
| 4.                                       | 1/2 sec, 30 PSI |            |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

