

Michilene F8230-03

Polypropylene Copolymer

API Polymers, Inc.

Message:

Michilene F8230-03 is a Polypropylene Copolymer (PP Copolymer) product. It is available in North America. Primary characteristic: copolymer.

General Information			
Features	Copolymer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.908	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	30	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.4	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	24.8	MPa	ASTM D638
Tensile Elongation (Break)	12	%	ASTM D638
Flexural Modulus - Tangent	1100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	91	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	87.8	°C	
1.8 MPa, Unannealed	54.4	°C	
Brittleness Temperature	-18.0	°C	ASTM D789
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	216	°C	
Middle Temperature	216	°C	
Front Temperature	210	°C	
Nozzle Temperature	204	°C	
Processing (Melt) Temp	216	°C	
Mold Temperature	26.7	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

