

Polifil® Nylon 620

Polyamide 66

The Plastics Group

Message:

Polifil® Nylon 620 is a Polyamide 66 (Nylon 66) product. It is available in North America. Typical application: Housings.

General Information			
Uses	Housings		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.015	%	ASTM D955
Water Absorption (24 hr)	1.5	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	75.8	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	4.0	%	
Break	30	%	
Flexural Modulus	2620	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	202	°C	
1.8 MPa, Unannealed	87.2	°C	
Melting Temperature	254	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Constant (1 MHz)	3.90		ASTM D150
Injection	Nominal Value	Unit	
Rear Temperature	282	°C	
Middle Temperature	274	°C	
Front Temperature	271	°C	
Nozzle Temperature	260 to 299	°C	
Processing (Melt) Temp	279 to 304	°C	
Injection Rate	Moderate-Fast		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

