

Lupoy® 1603-06

Polycarbonate
LG Chem Ltd.

Message:

LUPOY PC 1603-06 resin is designed for extrusion products. It exhibits an excellent physical property balance of heat resistance, transparency and impact strength.

General Information			
Additive	UV Stabilizer		
Features	Good Impact Resistance		
	Good Melt Strength		
	Good Mold Release		
	High Clarity		
	High Heat Resistance		
	High Viscosity		
Uses	Sheet		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption			ASTM D570
23°C, 24 hr	0.15	%	
Equilibrium, 23°C, 50% RH	0.32	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	60.0	MPa	
Break	56.0	MPa	
Tensile Elongation			ASTM D638
Yield	6.0	%	
Break	90	%	
Flexural Modulus	2300	MPa	ASTM D790
Flexural Strength	96.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ¹ (23°C, 3.20 mm)	890	J/m	ASTM D256
Unnotched Izod Impact (23°C)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 4.00 mm)	126	°C	ASTM D648

Vicat Softening Temperature	150	°C	ASTM D1525 ²
CLTE - Flow (-40 to 82°C)	6.8E-5	cm/cm/°C	ASTM D696
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance	89.0	%	ASTM D1003
Haze	0.70 to 1.5	%	ASTM D1003
NOTE			
1.	0.25 mm Notch Depth		
2.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

