

PLEXIGLAS® Sheet Optical RP Studio 7D006

Polymethyl Methacrylate Acrylic
Evonik Industries AG

Message:

PLEXIGLAS® RP was especially developed for rear projection to ensure optimal image generation in this demanding field of application. The base material is highly transparent PMMA with its excellent light transmission (92%). It offers very good mechanical strength, which makes the rear projection screens extremely hard-wearing.

General Information			
Features	High Clarity		
Uses	Electronic Displays		
	Lighting Diffusers		
	Optical Applications		
Appearance	Light Grey		
Forms	Sheet		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3300	MPa	ISO 527-2/1B/1
Tensile Stress ¹	72.0	MPa	ISO 527-2/5
Tensile Strain (Break)	4.5	%	ISO 527-2/1B/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.6	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	15	kJ/m²	ISO 179/1fU
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	105	°C	ISO 306/B
Optical	Nominal Value	Unit	Test Method
Gloss			ISO 2813
20°	3		
60°	20		
85°	20		
Transmittance	45.0	%	
Gain	1.00		
Half-Gain	38.0	°	
Water Uptake Properties (in liquid) - 24h	38.0	mg	ISO 62
NOTE			
1.	Type 1B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

