

VAMPAMID 66 2530 V0 P60

Polyamide 66

Vamp Tech

Message:

UL 94 V0 1,6 mm, 25 % glass fiber, red phosphorus, excellent mechanical properties, CTI 600 V.

General Information			
UL YellowCard	E140692-223037		
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.60	%	
Across Flow	1.0	%	
Water Absorption (Saturation)	0.90	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8000	MPa	ASTM D638
Tensile Strength (Yield)	115	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	8.0	kJ/m²	ISO 180/A
Unnotched Izod Impact Strength	45	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	235	°C	ASTM D648A
RTI Elec	120	°C	UL 746
RTI Imp	120	°C	UL 746
RTI Str	120	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Flammability Index (1.00 to 2.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	275	°C	
Mold Temperature	90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

