

Axiall PVC 28930

Flexible Polyvinyl Chloride

Axiall Corporation

Message:

Non lead stabilized 105C FT-4 riser jacket compound. UV resistant.

General Information			
Features	Good UV Resistance		
Uses	Cable Jacketing		
	Wire & Cable Applications		
Wire Types	FT-4		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39 to 1.43	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	90 to 96		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	20.7	MPa	ASTM D638
Tensile Elongation (Break)	280	%	ASTM D638
Aging	Nominal Value	Unit	Test Method
Change in Ultimate Elongation in Air (136168°C)	-32	%	ASTM D573
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	34	%	ASTM D2863
Extrusion	Nominal Value	Unit	
Melt Temperature	193	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT