

Pyramid™ PEEK CC200 (KD2190)

Polyetheretherketone

Polymics, Ltd.

Message:

PEEK with 60% Continuous Carbon Fiber

General Information			
Filler / Reinforcement	Carbon Fiber,60% Filler by Weight		
Appearance	Black		
	Grey		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm ³	ASTM D792
Water Absorption (24 hr)	< 0.10	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	112		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	52000	MPa	ASTM D638
Tensile Strength (Break)	565	MPa	ASTM D638
Tensile Elongation (Break)	0.90	%	ASTM D638
Flexural Modulus	45000	MPa	ASTM D790
Flexural Strength	330	MPa	ASTM D790
Compressive Strength	59.0	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.318 mm)	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	> 300	°C	ASTM D648
Glass Transition Temperature	143	°C	ASTM E1356
Melting Temperature	340	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 50	ohms	ASTM D257
Volume Resistivity	< 50	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

