

Leona™ 1402S

Polyamide 66

Asahi Kasei Chemicals Corporation

Message:

Leona™ 1402S is a Polyamide 66 (Nylon 66) product. It is available in Africa & Middle East, Asia Pacific, Europe, or North America. Applications of Leona™ 1402S include automotive, consumer goods, electrical/electronic applications and wire & cable.

Characteristics include:

- Flame Rated
- Good Stiffness
- Good Toughness
- Heat Stabilizer

General Information	
UL YellowCard	E48285-240893
Additive	Heat Stabilizer
Features	Good Flow
	Good Stiffness
	Good Toughness
	Heat Stabilized
Uses	Automotive Applications
	Connectors
	Consumer Applications
	Wire & Cable Applications

Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.14	--	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage - Flow	1.3 to 2.0	--	%	Internal Method
Water Absorption				
Saturation, 23°C	--	2.5	%	
Equilibrium, 23°C, 50% RH	--	2.5	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785, ISO 2039-2
M-Scale	80	55		
R-Scale	120	108		
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3000	1200	MPa	ISO 527-2
Tensile Stress				
Yield, 23°C	82.0	52.0	MPa	ISO 527-2
--	79.0	57.0	MPa	ASTM D638
Tensile Strain				

Yield, 23°C	4.0	24	%	ISO 527-2
Break	50	250	%	ASTM D638
Break, 23°C	--	> 100	%	ISO 527-2
Flexural Modulus				
--	2800	1200	MPa	ASTM D790
23°C	2700	1100	MPa	ISO 178
Flexural Strength				
--	118	54.0	MPa	ASTM D790
23°C	113	42.0	MPa	ISO 178
Taber Abrasion Resistance (1000 Cycles)	--	7.00	mg	ASTM D1044
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	6.0	15	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break	No Break		ISO 179
Notched Izod Impact	39	150	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	230	--	°C	ASTM D648
0.45 MPa, Unannealed	190	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	70.0	--	°C	ASTM D648, ISO 75-2/A
CLTE - Flow	8.0E-5	--	cm/cm/°C	ASTM D696
Specific Heat	1670	--	J/kg/°C	
Thermal Conductivity	0.20	--	W/m/K	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	--	ohms	ASTM D257, IEC 60093
Volume Resistivity				
--	1.0E+14	--	ohms·cm	ASTM D257
23°C	1.0E+14	--	ohms·cm	IEC 60093
Dielectric Strength	20	--	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (3.00 mm)	525	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	V-2	--		UL 94
Glow Wire Flammability Index (3.00 mm)	960	--	°C	IEC 60695-2-12
Oxygen Index	26	--	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

