

Cariflex® IR0307 K

Polyisoprene
Kraton Polymers LLC

Message:

Cariflex IR0307 KU polymer is a solution polymerised polyisoprene with a high cis-1,4 content. It has a high molecular weight as indicated by its Logarithmic Inherent Viscosity (LIV) value of 6.80 dl/g. It is supplied from North America in the physical form identified below.

Cariflex IR0307 KU - supplied as white/transparent solid bale.

A non-staining stabilizer is added at the typical value of 0.1%.

Cariflex IR0307 KU polymer is manufactured to the highest standards but special requirements apply to certain sensitive applications such as food contact and pharmaceuticals. Reference should always be made to local legislation regulating these applications.

Cariflex IR0307 KU Polymer is used as a replacement for natural rubber in a wide range of compounds, offering advantages of light color, uniformity and low levels of impurities. Its good flow characteristics produce improvements in mixing and molding behavior. It is used for food and pharmaceutical packaging and seals, baby bottle teats and health care, adhesives, chemical derivatives of rubbers and very light colored or transparent articles.

General Information			
Additive	Unspecified Stabilizer		
Features	Good Flow		
	High Molecular Weight		
	High Purity		
Uses	Adhesives		
	Food Packaging		
	Medical/Healthcare Applications		
	Pacifiers		
	Pharmaceutical Packaging		
	Rubber Replacement		
Appearance	Clear/Transparent		
	White		
Forms	Bale		
Physical	Nominal Value	Unit	Test Method
1,4-cis Content			Internal Method
-- ¹	> 82.0	wt%	
-- ²	> 90.0	wt%	
Ash Content	< 0.10	%	Internal Method
Limiting Viscosity Number	670 to 920	cm ³ /g	Internal Method
Stabilizer	0.060 to 0.12	%	Internal Method
Volatile Matter	< 0.50	%	Internal Method
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ³ (300% Strain)	8.60 to 13.5	MPa	ISO 37
Tensile Stress ⁴ (Yield)	> 21.6	MPa	ISO 37
Tensile Elongation ⁵ (Break)	> 430	%	ISO 37

NOTE	
1.	NMR
2.	FTIR
3.	Cure: 40 min at 135°C
4.	Cure: 40 min at 135°C
5.	Cure: 40 min at 135°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

