

POWERSIL® 732 CS A/B

Silicone
Wacker Chemie AG

Message:
Silicone Rubber, LSR
Cable Accessories, Electrical Industry
Cable Accessories, Energy & Electrical Engineering

General Information			
Features	Electrically Insulating		
	Tracking Resistant		
Uses	Extra High Voltage Insulation		
	High Voltage Insulation		
	Insulation		
	Low Voltage Insulation		
	Medium Voltage Insulation		
	Track Resistant Insulation		
Processing Method	Injection Molding		
Flammability	Nominal Value		Test Method
Flammability	FV 0		IEC 60707
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.11	g/cm ³	ISO 1183
Viscosity	330	Pa · s	ISO 3219
Pot Life	4300	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	33		ISO 868
Tensile Strength	9.00	MPa	ISO 37
Tensile Elongation at Break	740	%	ISO 37
Tear Strength	35.0	kN/m	ASTM D624B
Arc Resistance	420	sec	IEC 61621
Electric Strength	> 23	kV/mm	IEC 60243
Relative Permittivity	2.70		IEC 60250
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Dissipation Factor (50 Hz)	2.0E-4		IEC 60250
Tracking Resistance	1A 4.5		IEC 60587

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT