

Resirene READ 9500 RAF

High Impact Polystyrene

Resirene, S.A. de C.V.

Message:

Resirene READ 9500 RAF is an easy to process HIPS and is optimal for injection molding process.

General Information			
Features	Flame Retardant		
	High Flow		
	High Impact Resistance		
Uses	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1790	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	14.0	MPa	
Break	10.0	MPa	
Tensile Elongation			ASTM D638
Yield	1.0	%	
Break	35	%	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	120	J/m	ASTM D256
Flammability	Nominal Value		Test Method
Flame Rating (1.52 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	200 to 230	°C	
Middle Temperature	200 to 230	°C	
Front Temperature	200 to 230	°C	
Processing (Melt) Temp	< 240	°C	
Mold Temperature	240	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

