

Rilsan® BESN Noir P40 TL01

Polyamide 11

Arkema

Message:

Rilsan ® BESN Noir P40 TL01 is a polyamide 11 produced from a renewable source. This black grade is plasticized and designed for extrusion.

MAIN APPLICATIONS

Fluid transportation.

Tubing for use in motor vehicle.

General Information			
Additive	Plasticizer		
Features	Renewable Resource Content		
Uses	Automotive Applications		
	Tubing		
Appearance	Black		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore D	68		
Shore D, 15 sec	60		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	335	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	26.0	MPa	
Break	48.0	MPa	
Tensile Strain			ISO 527-2
Yield	50	%	
Break	> 200	%	
Flexural Modulus	300	MPa	ISO 178
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	7.00	mg	ISO 9352
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	7.0	kJ/m ²	
23°C	No Break		
Charpy Unnotched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		

Thermal	Nominal Value	Unit	Test Method
Melting Temperature	181	°C	ISO 11357-3
Additional Information	Nominal Value	Unit	Test Method
ISO Shortname	PA11-P, EHL, 22-003		ISO 1874
Renewable Carbon Content	> 89	%	ASTM D6866
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	4.0 to 8.0	hr	
Melt Temperature	230 to 280	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

